

CONCENTRATIONS AND RECOMMENDED MAXIMUM CONTINUOUS EXPOSURE TEMPERATURE - DEGREES F

CHEMICAL	CONC.%	NOTES	F010	F007	F080	F083	F085	F282	K190	F701	F737	Hood & Duct K733
			F013 K022	F015		K023	F086 K095		F707 F764 F774	TEMPERATURE		TEMPERATURE
HYDROXYACETIC ACID	35		100		100	100	150	140	140	120		140
HYDROXYACETIC ACID	70		100		100	100	100	100	100		NR	120
HYDROXYBENZENESULFONIC ACID	ALL		140				140	140		70		
HYPOCHLOROUS ACID	10		80		100		100	100	100		NR	105
HYPOPHOSPHOROUS ACID	50		120	80	90	90	120	120	110			
IODINE	CRISTALS		150	150			150	150				
IODINE	VAPOUR		150	150			180		180			180
ISOAMYL ALCOHOL	100	11	120	140	120	120	150	100	100	70		
ISOBUTYL ALCOHOL	ALL	11	120				150	120		120	NR	
ISODECANOL	20	11	140				150	150		140	NR	
ISODECANOL	100	11	120	120	180	180	180	150	150	140	NR	
ISONONYL ALCOHOL	100	11	150	150			150	150		140	NR	
ISOOCTYL ADIPATE	100		120	120			150	150			NR	
ISOOCTYL ALCOHOL	100	11	140	150			150	140		140	NR	
ISOPROPYL ALCOHOL	100	11	100	120			120	120		80	NR	
ISOPROPYL AMINE	100		NR	NR	NR	NR	70	NR	NR			
ISOPROPYL MYRISTATE	100		200	230			230	210				
ISOPROPYL PALMITATE	100		200	220	220		230	210		120	NR	180
ISOPROPYL SULFATE	ALL						80	80				
ITACONIC ACID	40		140				140	140				
ITACONIC ACID	SAT'D		120				120	120			NR	
JET FUEL AV GAS	100	10,11	140	140	120	120	140	120		120		
JET FUEL A AND A1	100	10,11	140	140	120	120	140	120		120		
JET FUEL B	100	10,11	100	140	120	120	140	120		120		
JET FUEL JP-4	100	10,11	100	120	120	120	120	120		120		
JET FUEL JP-8	100	10,11	100	120	120	120	120	120		120		
JET FUEL JP-10	100	10,11	100	120	120	120	120	120		120		
JOJOBA OIL	100		180				180	180				
KEROSENE	100	10,11	180	180	180	180	180	180	180	180	120	120
LACTIC ACID	10		180				180	180		140	120	
LACTIC ACID	80		80				80	80		80	80	
LATEX, ALKALINE	ALL		80				80	80				
LATEX, PAINT EMULSION	ALL		120	120			120	120			NR	
LATEX, PVA EMULSION	ALL		100	100			120	120				
LATEX, RUBBER EMULSION	ALL		100		100	120	120	120			NR	
LAURIC ACID	ALL		200	200	210		210	210		180	120	
LAUROYL ALCOHOL	100	11	200	200			200	200		80		
LAUROYL CHLORIDE	100		120				120	120				
LAURYL ALCOHOL	ALL	11	150	180	120	180	180	180	120	80		