

CONCENTRATIONS AND RECOMMENDED MAXIMUM CONTINUOUS EXPOSURE TEMPERATURE - DEGREES F

CHEMICAL	CONC.%	NOTES	F010	F007	F080	F083	F085	F282	K190	F701	F707	Hood & Duct K733
			F013 K022	F015	K023	F086 K095	F764 F774		F737			
			TEMPERATURE									
TRIPROPYL AMINE -N	ALL		80				80	80				
TRIPROPYLENE GLYCOL	100		210	210	210	210	210	210	250	180	130	180
TRISODIUM PHOSPHATE	ALL		210	210	210	210	210	210	150	NR	NR	
TRITOLYL PHOSPHATE	ALL		140				140	140				
TUNA OIL	ALL	12	200	210	200	200	210	210	200	160	120	180
TURPENTINE	100	11	150	210	150	120	210	150		80		90
TWEEN SURFACTANT	100		150				170	150				
URANIUM EXTRACTION			180	180	180	180	180	180	180	180	120	120
UREA	ALL		160	160	160	160	160	160	160	150		90
UREA / AMMONIUM NITRATE / WATER (35%/44%/21%)	100		150	150			150	150	120			
UREA FERTILIZER			150	150			150	150	120	120		
UREA FORMALDEHYDE RESINS PH<7	ALL		100	120			120	100	80			
VAR SOL SOLVENT	100	11	180	210			210	200	200	120	NR	
VEGETABLE OILS	ALL	12	200	200	200	200	210	210	200	160	80	160
VINEGAR	ALL	12	210	210	210	210	210	200	200	130	120	150
VINYL ACETATE	100		NR				NR	NR				
VINYL CHLORIDE	100		NR				NR	NR	90			
VINYL TOLUENE	100		NR	80	80	80	120	NR	80	NR	NR	
WATER, DEIONISED	100		180	170	180	180	180	180	180	150	120	
WATER, DEMINERALIZED	100		180	180	180	180	180	180	180	150	120	
WATER, DISTILLED	100		180	180	180	180	180	180	180	140	120	
WATER, SEA	100		180	180	180	180	180	180	180	150	140	140
WATER, STEAM CONDENSATE	100		180	180	180	180	180	180	180	150	120	
WHISKEY								110	NR	80	NR	
WHITE LIQUOR (PULP MILL)		10	180	180	150	180	100	190				
WINE								110		80	NR	
XYLENE	100	11	NR	80	100	100	120	120	100	90	NR	90
XYLENE (M-)	100	11	NR	80	100	100	120	120		90	NR	
XYLENE (O-)	100	11	NR	80	100	100	100	120		90	NR	
XYLENE (P-)	100	11	NR	80	100	100	100	120		90	NR	
ZEOLITE	ALL							210				
ZINC CHLORATE	ALL		200	180			210	210				
ZINC CHLORIDE	ALL		210	210			210	210	210	170	120	
ZINC CYANIDE	ALL		180	180	160	180	180	175	NR			90
ZINC NITRATE	ALL		210	210	210	210	210	210	180	170	120	180
ZINC SULPHATE	ALL		210	210	210	210	210	210	210	170	120	180
ZINC SULPHITE	ALL		200	160	180	180	210	210		140	100	150